

## CHEMAX SBR LETEX 51

Mortar bonding agent cum waterproofing agent



### CHEMAX SBR LATEX 51

High Range Mortar &  
Screen Modifier Cum Bonding Agent

#### DESCRIPTION:

For modifying and improving bonding of floor toppings, renderings and mortars; repair of worn, damaged and spalled concrete, repair of large cracks, polymer modified floor screeds, waterproof plasters for masonry and slurries.

#### ADVANTAGES:

1. Simple to use
2. High Adhesion
3. Improves Durability
4. Reduces permeability
5. Increases Strength
6. Versatile
7. Cost Effective
8. Waterproofing

#### PACKAGING:

250 ml, 500 ml, 1 ltr,  
5 ltr, 20 ltr, 50 ltr, 200 ltr

1800 - 419 - 3637





## CHEMAX SBR LETEX 51

Mortar bonding agent cum waterproofing agent

### Uses:

- For modifying and improving bonding of floor toppings, renderings and mortars; repair of worn, damaged and spalled concrete, repair of large cracks; polymer modified floor screeds; waterproof plasters for masonry and slurries.

### Advantages:

- Simple to use** - Single component, gauged as required.
- High adhesion** - Provides excellent bond to concrete, adhesion plaster, masonry, stonework, etc.
- Improves durability** - Gives weather resistant mortar with improved impermeability to chlorides and other harmful agents.
- Reduces permeability** - Provides waterproof screeds, plasters and permeability slurries.
- Increases strength** - Improved tensile and flexural properties allow thin applications.
- Versatile** - Compatible with all common hydraulic cements.
- Cost effective** - CHEMAX SBR LATEX 51 is economical to use
- Waterproofing** - CHEMAX SBR LATEX 51 is economical waterproofing agent.

### Description:

- CHEMAX SBR LATEX 51** is modified styrene butadiene rubber emulsion specially designed for use as a bonding aid and gauging liquid for cementations systems. It is resistant to hydrolysis and can therefore be used for external applications too.

### Properties :

- Specific gravity** 1.03 to 1.04 g/cc
- Typical mechanical properties of 1:3 cement sand mortar at W/C - 0.45 for control and W/C - 0.35 for mortar containing CHEMAX SBR LATEX 51 (5 liters / 50 kg cement). Tested in accordance with BS 6319 & wet cured.

Mechanical properties	Control	CHEMAX SBR LETEX 51
<b>Compressive strength (N/mm<sup>2</sup>)</b>		
3 days	11.5	14.5
7 days	13.0	17.5
28 days	22.0	27.0
<b>Tensile strength</b>		
(N/mm <sup>2</sup> ) @ 28 days	2.5	4
<b>Flexural strength</b>		
(N/mm <sup>2</sup> ) @ 28 days	5.0	7.8



## **CHEMAX SBR LATEX 51**

**Mortar bonding agent cum waterproofing agent**

**Note:** Increased dosages of **CHEMAX SBR LATEX 51** and further water reduction leads to improved Mechanical properties.

### **Chemical resistance:**

- Cements based materials have limited chemical resistance. The addition of **CHEMAX SBR LATEX 51** to cement mortars reduces permeability and therefore helps reduce the rate of attack by aggressive chemicals.

### **Application Instructions:**

#### **Surface Preparation:**

- The object of the surface preparation is to achieve a clean sound surface with a good mechanical key. All substrates should be cleaned and free of dust, plaster, oil, paint, grease, corrosion deposits, and any other deleterious substances. Laitance should be removed by mechanical means. Smooth substrates must be mechanically roughened e.g. by scrubbing, needle gun or grit blasting to provide an adequate key. Corroded reinforcing steel should be exposed around its full circumference and cleaned to remove all loose scale and corrosion deposits. It is always preferably to clean the steel to a bright condition. Use of emery cloth, grit or sand blasting is recommended.

#### **Priming:**

- Reinforcing steel must be primed with CHEMAX Primer immediately after cleaning. The concrete substrate should be thoroughly dampened with water and any excess water removed before being primed by thoroughly scrubbing in a slurry coat of 1 volume **CHEMAX SBR LATEX 51** to 1 volume water to 3 volumes fresh cement.
- In order to obtain a smooth consistency the cement should be blended slowly into the liquids. Stir frequently during use to offset settlement. Avoid 'puddling' of the slurry coat. The topping must be applied on to the wet slurry. If the slurry dries out it must be removed and the clean substrate reprimed.

**CHEMAX SBR LETEX 51**

Mortar bonding agent cum waterproofing agent

**Typical Mix designs:****1. Patching and repair mortars and plaster for masonry**

Cement	50 kg
Zone II sand	150 kg
CHEMAX SBR LATEX 51	5 - 9 liters
Recommended water addition	11 - 15 liters
Recommended thickness	8 to 30mm

**2. Heavy duty floor screeds**

Cement	50kg
3-6mm Granite chips	75 kg
Zone II sand	75 kg
CHEMAX SBRLATEX 51	5-9 liters
Recommended water addition	8-12 liters
Recommended thickness	10-25mm

The screed should be of a semi-dry cohesive consistency.

**Cleaning:**

- Tools and equipment should be washed with water immediately after use.

**Packaging:**

- CHEMAX SBRLATEX 51 is supplied in 1, 5, 20, 50, 230 kg containers.

**Coverage:**

- Slurry primer – approximately 4-5 m<sup>2</sup>/liter depending on substrate porosity.

**Storage:**

- Storage in must be room temperature ( 20<sup>0</sup>c to 42<sup>0</sup>c)

**Shelf life:**

- CHEMAX SBRLATEX 51 has a shelf life of 18 months if kept in a dry store in unopened condition.



## **CHEMAX SBR LETEX 51**

**Mortar bonding agent cum waterproofing agent**

### **Precautions**

#### **Health & Safety Instructions :**

- **CHEMAX SBR LATEX 51** should not come in contact with skin and eyes or be swallowed. Protective gloves and goggles should be worn during handling the product. If contact with skin occurs, wash well with soap and water. Eye contamination should be washed thoroughly with clean water and medical advice sought. If swallowed seek medical attention immediately - Do not induce vomiting.

#### **Fire:**

- **CHEMAX SBR LATEX 51** is non flammable.