



CX FASTSET AN

Chloride free accelerating admixture

CX FASTSET AN

Chloride free accelerating admixture



DESCRIPTION:

CX FASTSET AN is a chloride free accelerating admixture based on a combination of formate and nitrite salts.

PACKAGING: 50kg, 250 kg

 1800 - 419 - 3637



ADVANTAGES:

1. Particularly effective in assisting to offset the delaying effect of low temperatures on setting and strength gain
2. Accelerated setting gives added protection against early age frost attack
3. Also provides a degree of water reduction or increased workability
4. Suitable for use in bricklaying mortar
5. Chloride free, safe for use in REINFORCED CONCRETE



Office Address:
124. Avalon Business Hub, Katargam
Surat-3945004 (GUJARAT)-INDIA

CHEMAX CONSTRUCTION CHEMICAL PVT. LTD.

E-visit: www.chemaxchemical.com

Support : 1800 - 419-3637

Factory Address:
43-48. SAT SHREE SHYAM INDUSTRIES, NR
KOTHAVA GAM, KIM-394111, SURAT



CX FASTSET AN

Chloride free accelerating admixture

Description :

- **CX FAST SET AN** is a chloride free accelerating admixture based on a combination of format and **nitrite** salts. It is supplied as a straw colored solution that instantly disperses in water.
- **CX FAST SET AN** accelerates the early stages of cement hydration, producing a more rapid stiffening and allowing strength gain to commence at an earlier stage.
- This effect is particularly noticeable at low temperatures and is most significant in the first 24 hours after mixing.

Uses:

- To accelerate the stiffening and early strength gain of Portland cement concrete and mortar
- Typical applications include concrete or mortar placed in cold weather and precast concrete

Advantages:

- Particularly effective in assisting to offset the delaying effect of low temperatures on setting and strength gain
- Accelerated setting gives added protection against early age frost attack
- Also provides a degree of water reduction or increased workability
- Suitable for use in bricklaying mortar
- Chloride free, safe for use in **REINFORCED CONCRETE**

Standards compliance:

- **CX FAST SET AN** complies with BS 5075 Part 1 and with ASTM C494 as type C.

Technical support:

- CHEMAX provides a technical advisory service for on-site assistance and advice on admixture selection, evaluation trials and dispensing equipment.
- Technical data and guidance can be provided for admixtures and other products for use with fresh and hardened concrete.

Typical dosage:

- The optimum dosage of **CXFAST SETAN** to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use. This allows the optimization of admixture dosage and mix design and provides a complete assessment of the concrete mix. A starting point for such trials is to use a dosage within the normal typical range of 2.00 to 3.00 litres / 100 kg of cement.

Use at other dosages:



CX FASTSET AN
Chloride free accelerating admixture

- Dosages outside the typical range quoted above may be used if necessary and suitable to meet particular mix requirements, provided that adequate supervision is available.
- Compliance with requirements must be assessed through trial mixes. Contact the CHEMAX Technical Service Department for advice in these cases.

Properties:

- **Appearance :** Straw colored liquid
- **Specific gravity :** Typically 1.26 at 20°C
- **Chloride content :** Nil to BS 5075
- **Air entrainment :** Typically less than 1% additional air is entrained at normal dosages
- **Alkali content:** Typically less than 155.0 g. Na₂O equivalent / liter of admixture.

Instructions for use:

Compatibility:

- **CX FAST SET AN** is compatible with other CHEMAX admixtures in the same concrete mix. The admixtures must be added to the concrete separately with the mixing water and must not be directly mixed together prior to addition.
- The performance of concrete containing more than one admixture should be assessed by trial mixes to ensure the desired combination of effects is obtained.
- **CX FAST SET AN** is suitable for use with ordinary Portland cement. Contact the CHEMAX Technical Service Department for advice on use with sulphate resisting cements and cement replacement materials.

Durability:

- **CX FAST SET AN** has no detrimental effect on the protection given to embedded steel by the alkalinity of cement and is safe for use as an accelerator in situations where chloride containing admixtures cannot be used.

Dispensing:

- The correct quantity of **CX FAST SET AN** should be measured by means of a recommended dispenser. The admixture should then be added to the concrete with the mixing water to obtain the best results. Contact the CHEMAX Technical Service Department for advice regarding dispensing suitable equipment and its installation.

Effects of overdosing:



CX FASTSET AN

Chloride free accelerating admixture

- An overdose of double the intended amount of **CX FAST SET AN** may result in increased acceleration.
- In common with other accelerators this may slightly reduce the ultimate strength of the concrete. Testing has shown no detrimental effect on embedded steel even at four times overdose.

Curing:

- As with all structural concrete, good curing practice should be maintained. Water spray, wet hessian or a Redicure spray applied curing membrane should be used.
- Typical performance examples many variables in concreting materials and conditions can effect the selection and use of an admixture.
- Trials should be carried out using relevant materials and conditions in order to determine the optimum mix design and admixture dosage to meet specific requirements.
- Typical performance examples from evaluation studies of **CX FAST SET AN** are included on this data sheet. The values quoted are representative of results obtained and are provided as illustrations of performance.
- Because of the variability of concreting materials, the results should only be taken as typical of the performance to be expected. Results quoted in individual examples should not be taken as necessarily directly comparable with other examples given here or results quoted elsewhere for **CXFAST SETAN** or other products.

Limitations:

- **CX FAST SET AN** is most effective at low temperatures and early ages. Where compressive strength gain is the major requirement, and stiffening rates are less important, a more cost effective performance may be obtained through the use of a CHEMAX plasticiser or superplasticiser.
- Normal precautions for cold weather concreting should be followed where **CX FAST SET AN** is used.

Estimating:

- **CXFAST SETAN** is available in 20,50 AND 250 KG drums.

Storage:



CX FASTSET AN

Chloride free accelerating admixture

- **CX FAST SET AN** has a minimum shelf life of 12 months provided the temperature is kept within the range of 2°C to 50°C. Should the temperature of the product fall outside this range then the CHEMAX Technical Service Department should be contacted for advice.
- **CX FAST SET AN** is an oxidizing agent and should be stored away from reducing agents and combustible materials.
- Freezing point: Below -16°C.
- Crystallization may occur below -1°C. If crystallization does occur it is important that the product is reconstituted before use.

Precautions :

Health and safety:

- **CX FAST SET AN** is toxic and should not be swallowed or allowed to come into contact with skin and eyes. Wear suitable protective gloves and goggles. Splashes on the skin should be removed with water.
- In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - Do not induce vomiting.
- **CX FAST SET AN** is an oxidizing agent and must not be mixed with acids and other admixtures. Refer to "Instructions for use". For further information consult the Product Safety Datasheet available for this product.

Fire:

- **CX FAST SET AN** is water based and non-flammable but should be stored away from combustible materials.

Cleaning and disposal:

- Spillages of **CX FAST SET AN** should be absorbed onto sand, earth or vermiculite and transferred to suitable containers.
- Do not allow **CX FAST SET AN** to enter rivers or drains.
- The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority