



CX INJECT EP2

High strength, epoxy resin grout

Description :

- **CX INJECT EP2** is a solvent free epoxy resin grout designed for grouting of gap widths of 0.25 to 10mm. It is an all liquid system consisting of base and hardener.
- The components are supplied in the correct mix proportions designed for whole pack mixing on site. **Specification:** Where shown on the contract documents, the epoxy grout shall be **CX INJECT EP2** supplied by CHEMAX.
- It shall provide good general chemical resistance, and a 7 day compressive strength of at least 80 N/mm².

Uses:

- Provides a free flowing grout, for use where physical properties and chemical resistance of the hardened grout are of utmost importance. It is suitable for a wide range of heavy duty applications including:
 - Underplate grouting to substantial structural elements.
 - Base plate grouting in dynamic load situations such as turbines and other reciprocating machinery.
 - Heavy industrial applications in steelworks, refineries chemical plants and electroplating works.
 - Structural infill where very high strength is required.
 - Rail track applications, to support heavy cranes, or on transporter rails.

Advantages :

- **Excellent durability** - high compressive, flexural and tensile strengths ensure a long working life.
- **Cost effective** - high early strength gain promotes minimum downtime and early commissioning of plant.
- **User friendly** - simple, full pack mixing to ensure that the performance characteristics are achieved.
- **Versatile** - suitable for a wide range of loading situations including repetitive dynamic loads.
- **Excellent in service performance** - non-shrink capability ensures full surface to surface contact.

Properties:

- Pot life : **50 min. @ 27°C**
- Density : **approx. 1050 kg/m³**
- Tensile strength : **20 N/mm² @ 7 days**
- Flexural strength : **40 N/mm² @ 7 days**
- Compressive strength : **45 N/mm² @ 1 day 60 N/mm² @ 3 days 80 N/mm² @ 7 days**



CX INJECT EP2
High strength, epoxy resin grout

Instruction For Use Preparation :

Underplate grouting:

- The unrestrained surface area of the grout must be kept to a minimum. Generally, the gap between the perimeter formwork and the plate edge should not exceed 75 mm on the pouring side and 25 mm on the opposite side. Formwork on the flank sides should be kept tight to the plate edge. Air pressure relief holes should be provided to allow venting of any isolated high spots.

Formwork:

- The formwork should be constructed to be leak proof as EP2 Is a free flow grout. This can be achieved by using foam rubber strip or mastic sealant beneath the constructed formwork and between joints. For free flow grout conditions, it is essential to provide a hydrostatic head of grout. To achieve this feeding hopper should be used - please consult your local CHEMAX office for more details.

Foundation surface:

- This must be free from oil, grease, or any loosely adherent material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Bolt holes or fixing pockets must be blown clean of any dirt or debris.

Base plate:

- If delay is likely before placing steel base plates, it is recommended that the underside and edges are coated with CHEMAX SUPER CLEAN to prevent rust formation and ensure bonding with the **CX INJECT EP2** grout. All metal surfaces should be cleaned to a bright finish in accordance with Swedish Standard SA 2½ or equal. CHEMAX SUPER CLEAN can be applied directly onto newly cleaned steel surfaces even if they are damp.

Mixing:

- The entire contents of the hardener can should be poured into the base container and mixed for 2-3 minutes or until uniform color is achieved. Once mixed, the material must be used within the specified pot life (see under Properties). After this time, unused material will have stiffened and should be discarded.



CX INJECT EP2

High strength, epoxy resin grout

Note:

- Immediately prior to placement, all surfaces must be dry.

Placing:

- Ensure that the grout can be placed within its pot life. Continuous grout flow is essential. Sufficient grout must be available prior to starting and the time taken to pour a batch must be regulated to the time taken to prepare the next one. Pouring should be from one side of the void to eliminate air entrapment. The hydrostatic head must be maintained at all times so that a continuous grout front is achieved.

Cleaning:

- All tools and equipment should be cleaned immediately after use with CHEMCLEAN SOL.

Hot weather working:

- Whilst the performance of **CX INJECT EP2** at elevated temperatures is assured, application under such conditions can sometimes be difficult. It is therefore suggested that, for temperatures above 35°C, the following guidelines are used:
- 1) Store unmixed materials in a cool (preferably temperature controlled) environment, avoiding exposure to direct sunlight.
- 2) Keep mixing and placing equipment cool, arranging shade protection if necessary. It is especially important to keep cool those surfaces of the equipment which will come into direct contact with the material itself.
- 3) Try to eliminate application in the middle of the day, and certainly avoid application in direct sunlight.
- 4) Ensure that there are sufficient operatives available to complete application within the material's pot life.

Limitations:

- Grouts should not be placed in any unrestrained situation, i.e. base plate plinths, etc. Failure to comply may lead to crack development in the grout.

Estimating:

- **Supply: CX INJECT EP2: 5 +2 PACK**
CHEMAX SUPER CLEAN :1 & 5 KG



CX INJECT EP2
High strength, epoxy resin grout

Coverage:

- **CX INJECT EP2** 15 TO 17 M.SQ. Per Pack

Storage:

- When stored in warehouse conditions below 35⁰C, **CX INJECT EP2** will have a shelf life of 12 months.

Precautions Health and safety:

- Some people are sensitive to epoxy resin so gloves and a barrier cream. Work or similar should be used when handling these products. If contact with the resin occurs, it must be removed before it hardens with a resin removing cream. Follow by washing with soap and water. **Do not** use solvent. The use of goggles is recommended but should accidental eye contamination occur, wash thoroughly with plenty of clean water and seek medical treatment immediately.

Fire:

- **CX INJECT EP2** is flammable.

Flash points

- **CX INJECT EP2: 39°C**
CX INJECT EP2: 33°C Grout consistency